

tierTM

Fabulous, functional, forever.

TECHNICAL DATA SHEET 2022



A PRODUCT BY **EVA-LAST**[®]
INSPIRED BY NATURE, DESIGNED FOR LIFE.

www.tierflooring.com

MANUFACTURERS DETAILS
Date of Publication:
 January 2022

Product name: Eva-Last® TIER™ flooring products.

Manufacturers information: Eva-Last® Distributors, Room 1203, 12/F Tower 3, 33 Canton road, Tsimshatsui Hongkong, China.

Emergency contacts: +27 10 593 9220

Product information: +27 10 593 9220

TIER™ indoor flooring

Having over a decade of experience in the field of extrusion, Eva-Last® has adapted the technique to develop a revolutionary extruded stone plastic composite vinyl flooring.

Our aim is to continually strive to improve our products to give you the most cost-effective product packed with much more benefits in the long run. The manufacturing process also includes a new premixing technique and additional quality control procedure.

Surface properties

Property	Applicable standard	Applicable test method	Requirement	Result	Conclusion
Wear resistance	-	ISO 1518-1	≤ 0.015 g/1 000 rev	0.01 g	Pass
	EN 16511	EN 13329	≥ 4 000 cycles	≥ 4 000 cycles	Class 34, heavy commercial
	NALFA LF 01-2011	NALFA LF 01-2011	≥ 6 000 cycles	≥ 6 000 cycles	Class 4, heavy commercial
Scratch	-	ISO 1518-1	≥ 2 500 g	3 200 g	Pass
Surface bonding	NALFA LF 01-2011	EN311/NALFA LF 01-2011	≥ 1.25 N/mm ²	1.56 N/mm ²	Class 4, heavy commercial
Static load (250 lbs/115 kg)	NALFA LF 01-2011	ASTM F970	≥ 8 MPa	15 MPa	Class 4, heavy commercial
Residual indentation	ASTM F1700	ASTM F1914	≤ 8 % (140 lbs/63 kg)	1.70 %	Pass
	EN 16511	EN 433/ISO 24343-1	≤ 0.15 mm	0.03 mm	Class 34, heavy commercial
Impact resistance (big ball)	EN 16511	EN 13329	≥ 1 800 mm	> 1 800 mm	IC3, Class 34, heavy commercial
	NALFA LF 01-2011	NALFA LF 01-2011	≥ 1 400 mm	> 1 400 mm	Class 4, heavy commercial
Impact resistance (small ball)	EN 13329	EN438	≥ 15 N	23 N	IC3, Class 34, heavy commercial
	NALFA LF 01-2011	NALFA LF 01-2011	≥ 500 mm (19.7 in)	900 mm	Class 4, heavy commercial
Slip resistance	EN14041	EN 13893	DryCOF ≥ 0.3	0.51	Class DS
	-	ASTM C1028	≥ 0.5	0.62	Meet ADA recommendation
	-	D 51130	≥ R9	R9	Anti-slip resistance R9
Color fastness to light	EN 13329	ISO 105-B02:1994, Method 3a	≥ Grade 6	> 6	Pass
	NALFA LF 01-2011	NALFA LF 01-2011	Slight change only	Slight change only	Class 4, heavy commercial
Resistance to staining	EN 16511	EN 438-2	Group 1 and 2: grade 5, group 3: grade 4	Group 1 and 2: grade 5, group 3: grade 4	Class 34, heavy commercial
	ASTM F1700	ASTM F925	Slight change only	No change	Pass
	NALFA LF 01-2011	NALFA LF 01-2011	Slight change only	No change	Class 4, heavy commercial

Chemical properties

Property	Applicable standard	Applicable test method	Requirement	Result	Conclusion
Formaldehyde emission	CARB2	ASTM 6007	≤ 0.11 ppm Release ≤ 0.124 mg/m ³	Undetected	CARB2
	EN 14041	EN 717-1	Release ≤ 0.124 mg/m ³	Undetected	E0
VOC	Decret No2011-321	ISO 16000	TVOC < 1000 µg/m ³	31 µg/m ³	VOCA+
	DIBT	ISO 16000	TVOC < 1000 µg/m ³	29 µg/m ³	Meet AgBB requirement - U mark certified
	Floorscore	Californian 01350	Within CREL/TAC	26	Floorscore certified
Ortho-phthalates	Prop 65	Spectrometry	Ortho-phthalate free	Undetected	Ortho-phthalate free, Comply with Prop 65
Lead	CPSIA	CPSC-CH-E-1002-08	≤ 90 ppm	Undetected	Meet children toy regulation
PAHs	EU REACH regulation No. 1907/2006	Spectrometry and chromatography	< 1 mg/kg	0.7 mg/kg	Meets requirement of a product that can be placed in a mouth
PCP	EN 14041	EN 12673	< 1 ppm	Undetected	Pass
Substances of Very High Concern (SVHC) (mercury, chromium VI, Cadmium, SCCp, benzene, Xylene, tributyltin, etc)	EU REACH regulation No. 1907/2006	Spectrometry and chromatography	≤ 0.1 % (w/w)	Undetected	REACH compliant

Physical properties

Property	Applicable standard	Applicable test method	Requirement	Result	Conclusion
Heat exposure resistance 80°C/180°F	EN 16511	ISO 23999	ΔW/ΔL ≤ 0.25 %	0.03 %	Class 34, heavy commercial
	ASTM 1700	ASTM F2199	ΔW/ΔL ≤ 0.16 %	0.03 %	Pass
Dimensional variation (humidity change)	EN 16511	ISO 24339	ΔW/ΔL ≤ 0.15 %	ΔW/ΔL ≤ 0.01 %	Class 34, heavy commercial
Swelling after submersion in water	EN 16511	ISO 24336	≤ 12 %	0%	Class 34, heavy commercial
	NALFA LF 01-2011	NALFA LF 01-2011	≤ 12 %	0%	Class 4, heavy commercial
Impact sound reduction (IIC)	-	ASTM E492-09	-	IIC = 71	IIC = 71
Sound transmission reduction (STC)	-	ASTM E90-09	-	STC = 75	STC = 75
Locking strength (23°C)	EN 16511	ISO 24334	Long side ≥ 2.0 kN/m Short side ≥ 3.5 kN/m	Long side ≥ 6.3 kN/m, Short side ≥ 5.4 kN/m	Class 34, heavy commercial
Thermal conductivity	EN 14041	EN 12667	-	0.173 W/(mK)	Suitable for underfloor heating system
Thermal resistance (R value)	-	ASTM C518	-	0.58 m ² K/W	Suitable for underfloor heating system
Reaction to fire	EN 14041	EN 13051-1	-	CHF = 9.4 kW/m ²	Class Bfl - s1
Fire resistance (CHF)	-	ASTM E648/662	-	0.94 W/cm ²	Class 1

Acoustic properties

Property	Applicable standard	Applicable test method	Requirement	Result	Conclusion
Impact sound	ISO 717-2	ISO 10140-3	Application dependent	L _{n,w} = 51 dB	Application dependent
				C _i = 1 dB	
Impact sound reduction	ISO 717-2	ISO 10140-3	Application dependent	ΔL _w = 22 dB	Application dependent
				C _{1a} = -11 dB	
Impact sound reduction (IIC)	ASTM E492	ASTM E492-09	Application dependent	IIC = 71	Application dependent
Sound transmission reduction (STC)	ASTM E90	ASTM E90-09	Application dependent	STC = 75	Application dependent



OTHER INFORMATION

Document disclaimer

The provided information is offered in good faith as accurate, but without guarantee, Eva-Last® makes no warranties or representations of any kind (express or implied) about the accuracy, adequacy, currency or completeness of the information, or that it is suitable for the intended use. Compliance with this document does not guarantee immunity from breach of any statutory requirements, building codes or relevant standards. The final responsibility for the correct design and specification rests with the designer and, for its satisfactory execution, with the contractor. Appropriate warnings and safe handling procedures should be provided to handlers and users. While most data has been compiled from research, case histories, experience and testing, small changes in environment can produce marked differences in performance. The decision to use a material, and in what manner, is made at your own risk. The use of a material and method may therefore need to be modified to its intended end use and environment. Eva-Last®, its directors, officers or employees shall not be responsible for any direct, indirect or special loss or damage arising from, or as a consequence of, use of, or reliance upon, any information contained in this document or other documents referenced herein. Eva-Last® expressly disclaims any liability which is based on, or arises out of, the information or any errors, omissions or misstatements herein.

Utilisation disclaimer

Legislation may differ between jurisdictions. Before installing any Eva-Last® product, ensure that the application is rational and complies with the local regulations and building codes. Wherever necessary, consult a suitably qualified professional. Be sure to comply with material manufacturer specifications. Where manufacturers and building codes differ, revert to the building code requirements. Check that your choice of product is suitable for its intended application. For further product specification and information visit www.eva-last.com

Copyright

If reprinted or reproduced or utilised in any form Eva-Last® should be acknowledged as the source of the information.

Eva-Last® periodically updates the information contained in this document and that of the Eva-Last® documents that have been referenced herein. Before using this document, please refer to the Eva-Last® website (www.eva-last.com) for the most up to date documents. Please refer to the applicable websites for the most recent updates on information contained herein pertaining to other sources.